



SHAKUN POLYMERS LIMITED

SPL-ZHFR-6001XL



ZERO-HALOGEN LOW SMOKE FLAME RETARDANT COMPOUND

Description

SPL-ZHFR-6001 XL is a Zero Halogen, Low smoke, Flame Retardant, Silane grafted, moisture curable by addition of a catalyst masterbatch crosslinkable Compound for insulation / sheathing applications. It has good electrical properties and high thermal stress resistance. It is good for insulation of power, signal and control cables.

Specifications

Cables manufactured with **SPL-ZHFR-6001 XL** according to standard technology meet the following industrial cable specifications.

- | | |
|--------------------------|-----------------------|
| BS 7211 , EN 50363-5 EI5 | • IEC 60092/351 HF 90 |
| VDE 0207 / 23 HJ1 | • VDE 0250 / 503 HJ3 |

Features

SPL-ZHFR-6001 XL consists of special thermoplastic polymers, inorganic filler and other additives. It shows good processing and physical properties. Cross linking is activated by heat and moisture after extrusion.

SPL-ZHFR-6001 XL provides following properties

- Good abrasion resistance
- Excellent mechanical and Electrical Properties
- Zero Halogen acid gas generation
- Long-term reliability
- Good flame retardancy and low smoke

Properties

<i>Property</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical Value</i>
Density at 27°C	ASTM D 792	g/cm ³	1.40
Hardness	ASTM D 2240	Shore D	46
Tensile Strength at break (50 mm/min)	ASTM D 638	MPa	12
Elongation at Break (50 mm/min)	ASTM D 638	%	210
Change of Tensile Properties after heat ageing (7 days at 136°C)	ASTM D 638	%	± 25
Hot Set Elongation, at 200°C for 15 min. at 0.2 N/mm ² load	IEC 60811-2-1	%	70
Elongation after unloading (P.S)	IEC 60811-2-1	%	NIL
Limiting Oxygen Index	ASTM D 2863	% O ₂	32
Temperature Index	ASTM D 2863	° C	250
Smoke Density Rating	ASTM D 2843	%	<20
Halogen Acid Gas Generation	IEC 60754-1	%	<0.5
Test on Gases Evolved During Combustion pH.	IEC 60754-2	pH	5.5
Conductivity		μs / mm	8
Volume Resistivity	ASTM D 257	Ohm-cm	1 x 10 ¹⁴
Pressure Test at 100°C, 4 hrs	IEC 60811-3-1	%	40

*All Data on 1 mm Tape extruded at Temperatures between 130-160°C on Zones and 165-170°C on Crosshead and Die and then Cured in Water at temperature of 85°C

* Data should not be used for specification work.

Processing Techniques

Catalyst (CTMB-09) dosage is 3 - 5% by weight and blending must be done just before using (2-3 hours max.), preferably in the extruder hopper. Catalyst doesn't need any predrying.

In general, it is recommended that this product be processed using a low compression screw with a L/D of 20:1. Extrusion temperatures of 130 – 170°C on Zones, 165°C on Neck, 170°C on Crosshead, 175°C on Die are recommended. **Do not dry the compound under any circumstances.** SPL-ZHFR-6001 XL can be cross linked by immersion in hot water at a temperature of 80°C for a period of 3-4 hrs approx. This duration can be adjusted depending upon insulation thickness, reel size etc. [Specific recommendations for processing conditions can be determined only when the application and type of equipment are known]. Ensure that the layers of the core do not stick during corsslinking process. in case of self curing, time depends also on the specific ambient conditions.

Screw: Recommended ZHFR screw with low compression ratio 1.2 - 1.5:1

Colorability

SPL-ZHFR-6001 XL is a Colorable Compound with PE/EVA Based masterbatch.

Packaging

SPL-ZHFR-6001 XL is available in the form of free flowing pellets and supplied in bags which will be placed directly on wooden pallet, duly shrink wrapped, completely export worthy. Material will be supplied with net content of 880 Kgs as under.

28 Bags of 6001-XL @ 30 Kgs = 840 Kgs & 02 Bags of Catalyst (CTMB-09) @ 20 Kgs = 40 Kgs

Safety

SPL-ZHFR-6001 XL is not classified as a dangerous preparation.

The product is supplied in form of pellets of about 2 – 3 mm in size and can be readily handled with commercially available equipment. All handling and transport of the product may generate some dust and fines, which constitute a potential risk for dust explosion. Therefore, all instruments in the system should be properly grounded. Properly designed equipment and good storage will reduce the potential risk. Please, check and follow local disposal regulations!

Inhalation of any type of dust may irritate the air passages and should be avoided. For hot products: immediately immerse in or flush the affected area with large amounts of cold water to dissipate heat.

In case of adverse exposure to melting products formed at elevated temperatures, immediately remove, the affected victim from exposure.

Sweep up spilled granules and place in suitable containers for recycle or disposal. Consult an expert on disposal or recovered material and ensure conformity to local disposal regulations.

The product is intended for industrial use only. A Material Safety Datasheet is available on request. Please contact our Technical Team at SHAKUN POLYMERS LTD., for more details on various aspects of safety, recovery and disposal of the product.

This information is to the best of our knowledge accurate but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

SHAKUN POLYMERS LIMITED

Regd. Office : 501/502 Ivory Terrace, R.C. Dutt Road, Alkapuri, Baroda 390 007, India.

TEL: 00-91-265-2335537 / 2330920 - Fax: 00-91-265-2339402

Web Site : www.shakunpolymers.com Email : sales@shakunpolymers.com
