



## SHAKUN POLYMERS LIMITED



### SP-PESC-60 (S) SEMI-CONDUCTING INSULATION SHIELDING (STRIPPABLE) COMPOUND FOR MEDIUM VOLTAGE CABLE

#### **Description**

SP-PESC-60 (S) is a Semi Conducting Insulation Shielding Compound for Medium Voltage Power Cables. The material is suitable for steam and water curing and gives good strip force over a wide temperature range without tears. Further it is easy to process and has low volume resistivity.

#### **Specification**

SP-PESC-60 (S) meets the requirement of:

- ICEA S-66-524/NEMA WC7
- BS 6622
- IEC 60502
- IEC 60840

#### **Properties**

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical Value</i>
Melt Flow Index, 190 °C, 21.6 Kg.	ASTM D 1238	g/10 min.	10
Density at 27 °C	ASTM D 1505	g/cm <sup>3</sup>	1.13
Tensile Strength (25mm/min)	ASTM D 638	kg/cm <sup>2</sup>	100
Elongation (25mm/min)	ASTM D 638	%	200
Stripping Force	ASTM D 903	N	10 - 20
Shore D Hardness	ASTM D 2240	--	47
DC Volume Resistivity - at 23 °C - at 90 °C	ASTM D 257	ohm-cm ohm-cm	<50 <100

\*Tensile Properties on 1 mm Extruded Tape

\*Data should not be used for specification work

### ***Processing***

Semiconducting SP-PESC-60 (S) has been formulated to be easily extrudable using conventional polyethylene extrusion lines. For optimum extrusion result with SP-PESC-60 (S) use melt extrusion temperature in the range of 150 - 180 °C.

Specific processing condition can be determined only by trials on individual equipment.

Semiconducting SP-PESC-60 (S) absorbs moisture, which can result in porosity in the extrudate. It is therefore recommended that the compound be thoroughly dried prior to use, usually 2-4 hours in hopper drier at 60 - 65 °C.

### ***Shipment***

SP-PESC-60 (S) is available in the form of free flowing pellets and supplied in bags of moisture resistant material with a net content of 25 Kgs.

This information is to the best of our knowledge, accurate but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

---

---

#### **SHAKUN POLYMERS LIMITED**

Regd. Office: 501/502 Ivory Terrace, R.C. Dutt Road, Alkapuri, Baroda 390 005, India.

Phone 00-91-265-2335537 / 2330920 - Fax #: 00-91-265-2339402

Web Site: [www.shakunpolymers.com](http://www.shakunpolymers.com) Email: [sales@shakunpolymers.com](mailto:sales@shakunpolymers.com)

---