



SHAKUN POLYMERS LIMITED



SPL-VTEK-ST1 Sheathing Compound

Description

SPL-VTEK- ST1 is a PVC Compound for sheathing application in a wide variety of Power Cables and is formulated with a high quality resin with special plasticizers, stabilizers.

Specification

Cables manufactured with **SPL-VTEK- ST1** according to standard technology meet IEC 60502-1 Type ST1 , BS 7655 4.1 Type TM1 & IS : 5831 Type ST 1 Specifications.

Properties

Property	Test Method	Unit	Typical Value
Density	ASTM D 792	g/cm ³	1.52 ± 0.03
Hardness	ASTM D 2240	Shore A	90 ± 2
Tensile Strength	ASTM D 638	MPa	14.0
Elongation	ASTM D 638	%	230
Variation in i) Tensile Properties after Heat Ageing at 80°C for 7 days			
a) Tensile Strength	ASTM D 638	%	≤ 20
b) Elongation	ASTM D 638	%	≤ 20
Variation in ii) Tensile Properties after Heat Ageing at 100°C for 7 days			
a) Tensile Strength	ASTM D 638	%	≤ 25
b) Elongation	ASTM D 638	%	≤ 25
Loss of Mass at 80°C for 7 days	IEC 60811-3-2	mg/cm ²	≤ 1.5
Thermal Stability at 200°C	IEC 60811-3-2	Minutes	60
Hot Deformation Test 80°C, 4-6 Hrs - Depth of indentation	IEC 60811-3-1	%	40

* Press Sheet Conditions : 180°C, 10 min, 200kg / cm²
* Data should not be used for specification work

▣ Processing Techniques

SPL-VTEK- ST1 can be processed on any good extruder designed for PVC at temperatures in the range of 130°C-190°C. The screw must have a good homogenizing capacity.

▣ Colorability

SPL-VTEK- ST1 is a Colorable Compound and no detrimental effects on properties in presence of masterbatch colours. We suggest drying masterbatch before use.

▣ Packaging

SPL-VTEK- ST1 is available in the form of free flowing pellets and supplied in bags of moisture resistant material with a net content of 30 Kgs. Material also available in Jumbo Boxes with a net content of 900 Kgs.

▣ Safety

SPL-VTEK- ST1 is not classified as a dangerous preparation.

The product is supplied in form of pellets of about 3 – 4 mm in size and can be readily handled with commercially available equipment. All handling and transport of the product may generate some dust and fines, which constitute a potential risk for dust explosion. Therefore, all instruments in the system should be properly grounded. Properly designed equipment and good storage will reduce the potential risk. Please, check and follow local disposal regulations!

Inhalation of any type of dust may irritate the air passages and should be avoided. For hot products: immediately immerse in or flush the affected area with large amounts of cold water to dissipate heat. In case of adverse exposure to melting products formed at elevated temperatures, immediately remove the affected victim from exposure.

Sweep up spilled granules and place in suitable containers for recycle or disposal. Consult an expert on disposal or recovered material and ensure conformity to local disposal regulations.

The product is intended for industrial use only. A Material Safety Datasheet is available on request. Please contact our Technical Team of SHAKUN POLYMERS LTD., for more details on various aspects of safety, recovery and disposal of the product.

This information is to the best of our knowledge accurate but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. The typical values given do not constitute specification for the product but represent typical analytical values.

SHAKUN POLYMERS LIMITED

Address : Regd. Office

501/502 Ivory Terrace,
R.C. Dutt Road,
Alkapuri, Baroda 390 007, India.

Phone : 00-91-265-2335537 / 2330920

Fax : 00-91-265-2339402

Website : www.shakunpolymers.com

E-mail : sales@shakunpolymers.com